



TE-8

NONWOVEN GEOTEXTILE

PROPERTY	TEST METHOD	M.A.R.V. (Min. Avg Roll Value)
Weight (Typical)	ASTM D 5261	8.0oz/yd ² (271g/m ²)
Grab Tensile	ASTM D 4632	205 lbs (.911 kN)
Grab Elongation	ASTM D 4632	50%
Trapezoid Tear	ASTM D 4533	85 lbs (.378 kN)
CBR Puncture Resistance	ASTM D 6241	535 lbs (2.38 kN)
Mullen Burst	ASTM D 3786	400 psi (2756 kPa)
Permittivity*	ASTM D 4491	1.4 sec ⁻¹
Water Flow*	ASTM D 4491	90 gpm/ft ² (3657 L/min/m ²)
A.O.S.*	ASTM D 4751	80 U.S. Sieve (.180 mm)
U.V. Resistance	ASTM D 4355	70% / 500 hrs

*At the time of manufacturing. Handling, storage, and shipping may change these properties.

PACKAGING	
Roll Dimensions	12.5 x 360/15 x 300
Square Yards per Roll	500
Estimated Roll Weight – lbs	250

This data is provided for informational purposes only. *Titan Environmental Containment Ltd.* makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with *Titan Environmental Containment Ltd.* for current updates.

Titan Environmental Containment Ltd.

777 Quest Blvd, PO Box 9 • Ile des Chenes, Manitoba • R0A0T0 • CANADA

Phone: +1.204.878.3955 Fax: +1.204.878.3980 Toll Free: +1.866.327.1957