



TE-M100

MONOFILAMENT GEOTEXTILES

Titan's Monofilament Geotextiles are manufactured using high tenacity monofilament polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position. These fabrics offer optimum performance when used in stabilization applications. Produced from the first quality raw materials, they provide the perfect balance of strength and separation in styles capable of functioning exceptionally well in a wide range of performance requirements. They resist ultraviolet and biological degradation, rotting, and are chemically inert to any natural bases or acids.

PROPERTY	TEST METHOD	M.A.R.V. (Min. Avg Roll Value)
Weight (Typical)	ASTM D-5261	5.6 oz/yd ² (190 g/m ²)
Grab Tensile	ASTM D-4632	370 X 200 lbs (1.65 x .889 kN)
Grab Elongation	ASTM D-4632	15 %
Trapezoid Tear Strength	ASTM D-4533	115 X 75 lbs (0.51 X .33 kN)
CBR Puncture Resistance	ASTM D-6241	675 lbs (3.0 kN)
Permittivity*	ASTM D-4491	2.1 sec ⁻¹
Water Flow*	ASTMD-4491	100 gpm/ft ² (4074 L/min/m ²)
AOS*	ASTM D-4751	40 US Sieve (0.425 mm)
U.V. Resistance	ASTM D-4355	70%/500 hours

*At the time of manufacturing. Handling, storage, and shipping may change these properties.

PACKAGING	
Roll Dimensions – (W X L)	12 ft x 300 ft
Square yards per roll	400
Estimated Roll Weight	155 lbs

This data is provided for informational purposes only. *Titan Environmental Containment Ltd.* makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with *Titan Environmental Containment Ltd.* for current updates.

Titan Environmental Containment Ltd.

777 Quest Blvd, PO Box 9 • Ile des Chenes, Manitoba • R0A0T0 • CANADA

Phone: +1.204.878.3955 Fax: +1.204.878.3980 Toll Free: +1.866.327.1957