



TE-PC42

TURF REINFORCEMENT MAT

The Titan Environmental Containment TE-PC42 turf reinforcement matting from is manufactured from a composition of 67% polypropylene fiber and 33% coconut fiber stitched between a black UV stabilized polypropylene top net with a mesh size of 1.34 x 1.27 cm (0.53 x 0.5 in) and a black UV stabilized polypropylene bottom net with a mesh size of 1.59 x 1.59 cm (0.626 x 0.626 in). The "PC" and "4" represent the polypropylene and coconut fiber applied at a minimum of 400 g/m² (0.75 lbs/yd²) and the "2" represents that the mat is netted on the top and bottom sides. The TE-PC42 is a permanent turf reinforcement mat. The mat is sewn together on 38.1 mm (1.5 in) centers, with UV stabilized polypropylene black thread. Each roll of TE-PC42 is packaged in red shrink-wrap with yellow directional tape and includes installation instructions.

Index Test Results From Bench Scale Testing (TRI Environmental Labs or NTPEP)

Test Method – Description	Parameters	Test Result
ASTM D6566 – Mass per Unit Area	Index Test	10.8 oz/sq. yd.
ASTM D4355 – UV Stability	Index Test	86% at 500 hours
ASTM D6818 – Tensile Strength Machine Direction (MD)	Index Test	27.3 lb/in @ 38.6%
Transverse/Cross Direction (TD)	Index Test	15.7 lb/in @ 27.4%
ASTM D6525 – Thickness	Index Test	0.390 in
ASTM D6567 – Ground Cover/Light Penetration	Index Test	79.7%/20.3%
ECTC Method 3 – Determination of Unvegetated RECP Ability to Protect Soil from Hydraulically-Induced Shear Stresses Under Bench-Scale Conditions - ASTM D7207	Regression (power curve)	3.3 psf @ ½ in soil loss

Standard Roll Details

Width	2.44m (8ft)	4.88m (16ft)
Standard Length	25.7m (84.3ft)	25.7m (84.3ft)
Area	62.7m ² (75yd ²)	125.4m ² (150yd ²)
Weight ±10%	28kg (61lb)	56kg (122lb)

Titan Environmental Containment Ltd.

777 Quest Blvd • Ile des Chenes, Manitoba • R0A0T0 • CANADA
Phone: +1.204.878.3955 Fax: +1.204.878.3980 Toll Free: +1.866.327.1957