



TITAN SKRIM

STRING REINFORCED

POLYETHYLENE

PROPERTIES	TEST METHOD	TSRP 20BB	TSRP 30BB
Appearance		Black/Black	Black/Black
Weight Per MSF (lbs)		76	140
Thickness (Nominal)		20 mil	30 mil
Elongation @ Max Load %			
Diagonal A	ASTM D7003	809%	726%
Diagonal B		697%	748%
Grab Tensile (lbs)			
Diagonal A	ASTM D7004	159	220
Diagonal B		160	220
Trapezoidal Tear (lbs)			
Diagonal A	ASTM D4533	76	144
Diagonal B		72	146
Hydrostatic Resistance	ASTM D751, Procedure A	177 psi	142 psi

Note: Test results were compiled by an independent laboratory. Results listed are the mean results of these tests.

This data is provided for informational purposes only. *Titan Environmental Containment Ltd.* makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with *Titan Environmental Containment Ltd.* for current updates.

Titan Environmental Containment Ltd.
 777 Quest Blvd • Ile des Chenes, Manitoba • R0A0T0 • CANADA
 Phone: +1.204.878.3955 Fax: +1.204.878.3980 Toll Free: +1.866.327.1957